

DATA SHEET

ECOSEAL – Natural Stone sealer - 0 VOC's. (High solids)

DESCRIPTION

A safe ORGANIC SOLVENT FREE Natural Stone sealer
A single part acrylic co-polymer resin suspended in a non organic solvent
Prevents penetration of dirt, oil and fuels
Protects against frost and reduces surface deterioration
Environmentally friendly
Inhibits weed, moss, algae and fungus growth

USE (exterior and interior)

Ready to use for sealing Sandstone, Limestone, Slate and Granite slabs or blocks
Not for use on polished stone

COLOUR

Milky in appearance and becomes clear as product dries. Enhances colour slightly

PACK SIZE

20 litre UN containers

SURFACE FINISH

Matt (slight sheen) 2 coats
Glossier effect 3+ coats

SPREADING RATE

Depending on surface type, porosity and application method
2 coats for best results
80-100 sq mtr per 20ltr when spraying, more when brushing or rolling

DRYING TIME

Dry to walk on usually within 2hr - During normal temps' 10°C+
Lower temps and areas in the shade will extend drying time
Recoat when dry
Do not park vehicles on surface for 48 hrs
Full cure approximately 7-10 days

PREPARATION

All surfaces must be clean, dry and be free from loose and flaking material, dirt, grease and vegetative growth.

APPLICATION

Course droplet low level spray, broom, brush or roller
*Avoid over flooding surface
* Brush, broom or roller out pooled sealer
Do not leave pooled sealer to cure

CLEANING - For cleaning equipment use water

PRECAUTIONS

Wear gloves and eye protection
In case of contact with eyes, rinse immediately with water and seek medical advice

Remove splashes from the skin with soap and water
Keep out of reach of children

GENERAL INFORMATION

ODOURLESS

NON FLAMMABLE

NON HAZARDOUS

0 VOC'S

Do not use below 8 °C. Protect stored product from frost and freezing

Do not seal wet or damp surfaces

Do not start sealing if rain is imminent

Do not use chlorine, bleach, sodium hypochlorite, acid, Paveclear or Paveclean chemicals prior to sealing with ECOSEAL – Natural Stone sealer

The specification and coverage rates are given in good faith and are based on our experience and knowledge but without liability

As Sealers Direct has no direct control over the methods employed by the user in applying its products, any warranty either written or implied is given in good faith and can only cover the material itself

If in doubt regarding any of the above points please contact us

A Material Safety Data Sheet is available on request

www.sealersdirect.co.uk